

ALUMINUM ALLOY PLATE SUPERIOR IN PRESS FORMABILITY

Patent number: JP2001342577
Publication date: 2001-12-14
Inventor: MORI YOICHIRO; FUJII SHIRO; SATO YUICHI;
TAKADA TAKESHI; TAWA TSUTOMU; KODA
CHIKAKO; HIRATA FUMIAKI
Applicant: NIPPON STEEL CORP; MITSUI TAKEDA CHEMICALS
INC
Classification:
- International: C23C26/00; B05D7/14; B32B15/08; C22C21/02;
C22C21/06
- european:
Application number: JP20000167216 20000605
Priority number(s): JP20000167216 20000605

Report a data error here

Abstract of JP2001342577

PROBLEM TO BE SOLVED: To provide a specified urethane coated aluminum alloy plate superior in press formability. **SOLUTION:** Aluminum alloy plate superior in press formability is characterized by providing an alkaline soluble type of lubrication coating with a film thickness of 0.5-10 μ m on its both sides or one side, which mainly consists of a polyurethane composition (A), of which the hydrophilic group is a carboxyl group or a sulfonate group with an acid value in the range of 30-180 and a neutralizer of the hydrophilic group is sodium hydroxide or potassium hydroxide, and a lubrication functionalization agent (B) of 1-30 weight % against the polyurethane composition; along with prescribing an alloy composition and a value of difference (TS-YS) between a tensile strength (TS) before press forming and 0.2% yield strength (YS). The alkaline soluble type of lubrication coating preferably further includes silica particles (C) of 1-30 weight % against the polyurethane composition, as a main component.

Data supplied from the **esp@cenet** database - Worldwide